



Elasto-Deck 6500 PT (Pedestrian Traffic System)

40 Mils DFT

**BROADCAST AND BACK ROLL COAT:
ELASTO-DECK 6500**

4

- 80 Sq ft per gallon (20 Mils DFT)
- Broadcast aggregate 12-15 per 100 Sq ft Uniformly (Not to refusal) and back roll

**BASE COAT:
ELASTO-DECK 6500**

3

- 80 Sq ft per gallon (20 Mils DFT)

**PRIMER COAT:
ELASTO-POXY PRIMER VOC OR W.B.**

2

- 250 Sq ft per gallon (4 Mils DFT)

1 CONCRETE SUBSTRATE

(Prep surface, detail cracks, penetrations and flashing)

