Technical Detail Drawing

Elasto-Deck 6500 VT (Vehicular Traffic System)

60-80 Mils DFT

4 BROADCAST COAT: ELASTO-DECK 6500

- 80 Sq ft per gallon (20 Mils DFT)
- Broadcast aggregate to refusal

5 DOUBLE BROADCAST COAT: ELASTO-DECK 6500

- 80 Sq ft per gallon (20 Mils DFT)
- Broadcast aggregate to refusal
- Turn radius & ramp areas

3 BASE COAT: ELASTO-DECK 6500

- 80 Sq ft per gallon (20 Mils DFT)

6 TOP COAT: ELASTO-DECK 6500

- 80 Sq ft per gallon (20 Mils DFT)



2 PRIMER COAT: ELASTO-POXY PRIMER VOC OR W.B.

- 250 Sq ft per gallon (4 Mils DFT)

1 CONCRETE SUBSTRATE

(Prep surface, detail cracks, penetrations and flashing)